

**Amendment to the Claims:**

This listing of claims will replace all prior versions, and listings of claims in the application:

**Listing of Claims:**

Claim 1-9 (Cancelled).

Claim 10. (Previously Presented): The method of Claim 21 wherein C is a diepoxide.

Claim 11. (Cancelled).

Claim 12. (Previously Presented): The method of Claim 22 wherein C is a diepoxide.

Claim 13. (Previously Presented): A molded article obtained by the method of Claim 19.

Claim 14. (Previously Presented): A molded article obtained by the method of Claim 20.

Claim 15. (Previously Presented): A molded article obtained by the method of Claim 21.

Claim 16. (Previously Presented): A molded article obtained by the method of Claim 22.

Claim 17-18 (Cancelled).

Claim 19. (Currently Amended): A method of using a reinforced molding compositions wherein the resin is at least one member selected from the group consisting of (co)polyamide 6 and ~~(co)polyamide 66~~, (co)polyamide 6,6 the Mo-7058

composition characterized in that its viscosity at a shear velocity of  $10 \text{ s}^{-1}$  is greater than  $1000 \text{ s}^{-4} \text{ Pas}$ , and at a shear velocity of  $1000 \text{ s}^{-1}$  its viscosity is less than  $300 \text{ Pas}$  at a processing temperature that is 40 to  $80^\circ\text{C}$  above the melting point of the molding composition, said method comprising preparing an article by thermoforming.

Claim 20. (Previously Presented): The method of Claim 19 wherein the viscosity is greater than  $1500 \text{ Pas}$  at shear velocity of  $10 \text{ s}^{-1}$  and is less than  $280 \text{ Pas}$  at shear velocity of  $1000 \text{ s}^{-1}$ .

Claim 21. (Previously Presented): The method of Claim 19 wherein the composition comprise A) 98 to 41 parts by weight of said resin and B) 2 to 50 parts by weight of reinforcing materials, and C) 0.1 to 4 parts by weight of branching additives and/or additives raising the molecular weight and D) 0 to 5 parts by weight of further additives, the sum of the parts by weight of A, B, C, D totaling 100.

Claim 22. (Previously Presented): The method of Claim 19 wherein the composition comprise A) 67 to 85 parts by weight of said resin and B) 15 to 30 parts by weight of reinforcing materials, and C) 0.2 to 1 part by weight of branching additives and/or additives raising the molecular weight, D) 0.1 to 2 parts by weight of further additives, the sum of the parts by weight of A, B, C and D totaling 100.